


AMENDMENTS TO THE CLAIMS


1. (CURRENTLY AMENDED) A water-soluble polymer dispersion in which a water-soluble polymer having at least one type of ionicity selected from among cationicity, an amphotericity, a nonionicity and an anionicity and occurring as fine particles with a particle size of not greater than 100  $\mu$ m and a polyalkylenimine and/or a modified polyalkylenimine in the sulfate salt form coexist, if necessary together with a necessary amount of a water-soluble inorganic salt.

2. (CURRENTLY AMENDED) A water-soluble polymer dispersion according to Claim 1, wherein the water-soluble polymer having at least one type of ionicity selected from among said cationicity and said amphotericity and occurring in the form of fine particles is produced by dispersion polymerization of a monomer (or monomer mixture) comprising 5 to 100 mole percent of a monomer represented by the general formula (1) and/or (2) given below, 0 to 50 mole percent of a monomer represented by the general formula (3) given below and 0 to 95 mole percent of a water-soluble nonionic monomer with stirring in the presence of said polyalkylenimine and/or modified polyalkylenimine in the sulfate salt form, if necessary further in the presence of a necessary amount of a water-soluble inorganic salt.




## General formula (1)

(In the general formula (1), R<sub>1</sub> is a hydrogen atom or a methyl group, R<sub>2</sub> and R<sub>3</sub> may be the same or different and each is an alkyl or an alkoxy group containing 1 to 3 carbon atoms or a benzyl group, R<sub>4</sub> is a hydrogen atom, an alkyl or alkoxy group containing 1 to 3 carbon atoms or a benzyl group. A represents an oxygen atom or NH, B represents an alkylene or an alkoxy group containing 2 to 4 carbon atoms, and X<sub>1</sub> represents an anion.)



## General formula (2)

(In the general formula (2),  $R_5$  represents a hydrogen atom or a methyl group,  $R_6$  and  $R_7$  each represents an alkyl or an alkoxy group containing 1 to 3 carbon atoms or a benzyl group, and  $X_2$  represents an anion.)




General formula (3)


(In the general formula (3),  $R_8$  represents a hydrogen atom, a methyl group or a carboxymethyl group, Q represents  $\text{SO}_3$ ,  $\text{C}_6\text{H}_4\text{SO}_3$ ,  $\text{CONHC}(\text{CH}_3)_2\text{CH}_2\text{SO}_3$ ,  $\text{C}_6\text{H}_4\text{COO}$  or  $\text{COO}$ ,  $R_9$  represents a hydrogen atom or  $\text{COOY}_2$ , and  $\text{Y}_1$  or  $\text{Y}_2$  represents a hydrogen atom or a cation.)

3. (CURRENTLY AMENDED) A water-soluble polymer dispersion according to Claim 1, wherein the water-soluble polymer having at least one type of ionicity selected from among said anionicity and said nonionicity and occurring in the form of fine particles is produced by dispersion polymerization of a monomer composition (mixture) comprising at least one monomer selected from among monomers represented by said general formula (3) given above and water-soluble nonionic monomers in the presence of said polyalkylenimine and/or modified polyalkylenimine in the sulfate salt form, if necessary further in the presence of a necessary amount of a water-soluble inorganic salt.

4. (CURRENTLY AMENDED) A water-soluble polymer dispersion according to any of Claims 1 to 3, wherein said modified polyalkylenimine has a structural unit represented by the general formula (4) and/or (5) given below.



General formula (4)




General formula (5)


(In the general formulas (4) and (5), p is an integer of 0 to 20, R<sub>10</sub> to R<sub>17</sub> each represents a hydrogen atom or an alkyl or hydroxyalkyl group containing 1 to 3 carbon atoms or a benzyl group, and X<sub>3</sub> to X<sub>6</sub> each is an anion.)

5. (CURRENTLY AMENDED) A water-soluble polymer dispersion according to any of Claims 1 to 4, wherein said modified polyalkylenimine comprises the reaction product

from a polyalkylenimine or a mixture of a polyalkylenimine and a polyamine and a polycationic substance represented by the general formula (6) and/or (7) given below.



General formula (6)



General formula (7)


(In the general formulas (6) and (7), P is an epoxy group or a halohydrin group, p is an integer of 0 to 20, R<sub>18</sub> to R<sub>26</sub> each is a hydrogen atom, an alkyl or hydroxyalkyl group containing 1 to 3 carbon atoms or a benzyl group, and X<sub>7</sub> to X<sub>10</sub> each is an anion.)

6. (CURRENTLY AMENDED) A water-soluble polymer dispersion according to ~~any~~ of Claims 1 to 4, wherein said modified polyalkylenimine is crosslinked by means of a polycationic substance represented by the general formula (6) given above.

7. (CURRENTLY AMENDED) A water-soluble polymer dispersion according to ~~any~~ of Claims 1 to 6, wherein the polyalkylenimine is polyethylenimine.

8. (CURRENTLY AMENDED) A water-soluble polymer dispersion according to ~~any~~ of Claims 1 to 7, wherein the polyalkylenimine and/or modified polyalkylenimine amounts to 20 to 200% by mass relative to the water-soluble polymer having at least one type of ionicity selected from among said cationicity, said amphotericity, said nonionicity and said anionicity.


9. (CURRENTLY AMENDED) A method of producing water-soluble polymer dispersions, wherein a dispersion of fine particles of a polymer having at least one type of ionicity selected from among cationicity and amphotericity is produced by subjecting a monomer (or monomer mixture) comprising 5 to 100 mole percent of a monomer represented by the general formula (1) and/or (2) given below, 0 to 50 mole percent of a monomer represented by the general formula (3) given below and 0 to 95 mole percent of a water-soluble nonionic monomer to dispersion polymerization with stirring in the presence of a polyalkylenimine and/or a modified polyalkylenimine in the sulfate salt form, if necessary further in the presence of a necessary amount of a water-soluble inorganic salt.



General formula (1)


(In the general formula (1), R<sub>1</sub> is a hydrogen atom or a methyl group, R<sub>2</sub> and R<sub>3</sub> may be the same or different and each is an alkyl or alkoxy group containing 1 to 3 carbon atoms or a benzyl group, R<sub>4</sub> is a hydrogen atom, an alkyl or alkoxy group containing 1 to 3 carbon atoms or a benzyl group. A represents an oxygen atom or NH, B represents

an alkylene or alkoxyethylene group containing 2 to 4 carbon atoms, and X<sub>1</sub> represents an anion.)



General formula (2)


(In the general formula (2), R<sub>5</sub> represents a hydrogen atom or a methyl group, R<sub>6</sub> and R<sub>7</sub> each represents an alkyl or alkoxy group containing 1 to 3 carbon atoms or a benzyl group, and X<sub>2</sub> represents an anion.)



General formula (3)

(In the general formula (3), R<sub>8</sub> represents a hydrogen atom, a methyl group or a carboxymethyl group, Q represents SO<sub>3</sub>, C<sub>6</sub>H<sub>4</sub>SO<sub>3</sub>, CONHC(CH<sub>3</sub>)<sub>2</sub>CH<sub>2</sub>SO<sub>3</sub>, C<sub>6</sub>H<sub>4</sub>COO or COO, R<sub>9</sub> represents a hydrogen atom or COOY<sub>2</sub>, and Y<sub>1</sub> or Y<sub>2</sub> represents a hydrogen atom or a cation.)

10. (CURRENTLY AMENDED) A method of producing water-soluble polymer dispersions, wherein a dispersion of fine particles of a polymer having at least one type of ionicity selected from among anionicity and nonionicity is produced by subjecting a monomer composition (mixture) comprising at least one monomer selected from among monomers represented by the general formula (3) given below and water-soluble nonionic monomers to dispersion polymerization with stirring in the presence of a polyalkylenimine and/or a modified polyalkylenimine in the sulfate salt form, if necessary further in the presence of a necessary amount of a water-soluble inorganic salt.



General formula (3)

(In the general formula (3), R<sub>8</sub> represents a hydrogen atom, a methyl group or a carboxymethyl group, Q represents SO<sub>3</sub>, C<sub>6</sub>H<sub>4</sub>SO<sub>3</sub>, CONHC(CH<sub>3</sub>)<sub>2</sub>CH<sub>2</sub>SO<sub>3</sub>, C<sub>6</sub>H<sub>4</sub>COO or COO, R<sub>9</sub> represents a hydrogen atom or COOY<sub>2</sub>, and Y<sub>1</sub> or Y<sub>2</sub> represents a hydrogen atom or a cation.)

11. (CURRENTLY AMENDED) A method of using the water-soluble polymer dispersion according to any of Claims 1 to 8 and 33 to 35, wherein the water-soluble polymer dispersion is added to paper stuff before papermaking for pretreatment thereof.

12. (CURRENTLY AMENDED) A method of using the water-soluble polymer dispersion according to any of Claims 1 to 8 and 33 to 35, wherein the water-soluble polymer dispersion is added to paper stuff before papermaking to thereby improve the freeness thereof.



13. (CURRENTLY AMENDED) A method of using the water-soluble polymer dispersion according to any of Claims 1 to 8 and 33 to 35, wherein the water-soluble polymer dispersion is added to paper stuff before papermaking, in which a sizing agent coexists, to thereby improve the degree of sizing.


14. (CURRENTLY AMENDED) A method of using the water-soluble polymer dispersion according to any of Claims 1 to 8 and 33 to 35, wherein the water-soluble polymer dispersion is added to paper stuff before papermaking to thereby improve the yield, followed by papermaking.

15. (CURRENTLY AMENDED) A method of using the water-soluble polymer dispersion according to any of Claims 1 to 8 and 33 to 35, wherein the water-soluble polymer dispersion is added to paper stuff before papermaking in combination with an inorganic and/or organic anionic substance to thereby improve the yield, followed by papermaking.


16. (CURRENTLY AMENDED) A method of using the water-soluble polymer dispersion according to any of Claims 1 to 8 and 33 to 35, wherein the water-soluble polymer dispersion is added to organic sludge or paper mill-derived sludge to cause flocculation, followed by dewatering by means of dewatering equipment.

17. (CURRENTLY AMENDED) A method of using the water-soluble polymer dispersion according to any of Claims 1 to 8 and 33 to 35, wherein the water-soluble polymer dispersion is added to organic sludge or paper mill-derived sludge in combination with an amphoteric or anionic water-soluble polymer to cause flocculation, followed by dewatering by means of dewatering equipment.

18. (NEW) A water-soluble polymer dispersion according to Claim 2, wherein said modified polyalkylenimine has a structural unit represented by the general formula (4) and/or (5) given below.




General formula (4)




General formula (5)

(In the general formulas (4) and (5), p is an integer of 0 to 20, R<sub>10</sub> to R<sub>17</sub> each represents a hydrogen atom or an alkyl or hydroxyalkyl group containing 1 to 3 carbon atoms or a benzyl group, and X<sub>3</sub> to X<sub>6</sub> each is an anion.)

19. (NEW) A water-soluble polymer dispersion according to Claim 2, wherein said modified polyalkylenimine comprises the reaction product from a polyalkylenimine or a mixture of a polyalkylenimine and a polyamine and a polycationic substance represented by the general formula (6) and/or (7) given below.



General formula (6)




General formula (7)


(In the general formulas (6) and (7), P is an epoxy group or a halohydrin group, p is an integer of 0 to 20, R<sub>18</sub> to R<sub>26</sub> each is a hydrogen atom, an alkyl or hydroxyalkyl group containing 1 to 3 carbon atoms or a benzyl group, and X<sub>7</sub> to X<sub>10</sub> each is an anion.)

20. (CURRENTLY AMENDED) A water-soluble polymer dispersion according to Claim 4, wherein said modified polyalkylenimine comprises the reaction product from a

polyalkylenimine or a mixture of a polyalkylenimine and a polyamine and a polycationic substance represented by the general formula (6) and/or (7) given below.



General formula (6)



General formula (7)

(In the general formulas (6) and (7), P is an epoxy group or a halohydrin group, p is an integer of 0 to 20, R<sub>18</sub> to R<sub>26</sub> each is a hydrogen atom, an alkyl or hydroxyalkyl group containing 1 to 3 carbon atoms or a benzyl group, and X<sub>7</sub> to X<sub>10</sub> each is an anion.)

21. (NEW) A water-soluble polymer dispersion according to Claim 2, wherein said modified polyalkylenimine is crosslinked by means of a polycationic substance represented by the general formula (6) given above.

22. (NEW) A water-soluble polymer dispersion according to Claim 4, wherein said modified polyalkylenimine is crosslinked by means of a polycationic substance represented by the general formula (6) given above.
23. (NEW) A water-soluble polymer dispersion according to Claim 2, wherein the polyalkylenimine is polyethylenimine.
24. (NEW) A water-soluble polymer dispersion according to Claim 4, wherein the polyalkylenimine is polyethylenimine.
25. (NEW) A water-soluble polymer dispersion according to Claim 5, wherein the polyalkylenimine is polyethylenimine.
26. (NEW) A water-soluble polymer dispersion according to Claim 6, wherein the polyalkylenimine is polyethylenimine.
27. (NEW) A water-soluble polymer dispersion according to Claim 2, wherein the polyalkylenimine and/or modified polyalkylenimine amounts to 20 to 200% by mass relative to the water-soluble polymer having at least one type of ionicity selected from among said cationicity, said amphotericity, said nonionicity and said anionicity.
28. (NEW) A water-soluble polymer dispersion according to Claim 4, wherein the polyalkylenimine and/or modified polyalkylenimine amounts to 20 to 200% by mass relative to the water-soluble polymer having at least one type of ionicity selected from among said cationicity, said amphotericity, said nonionicity and said anionicity.
29. (NEW) A water-soluble polymer dispersion according to Claim 5, wherein the polyalkylenimine and/or modified polyalkylenimine amounts to 20 to 200% by mass

relative to the water-soluble polymer having at least one type of ionicity selected from among said cationicity, said amphotericity, said nonionicity and said anionicity.

30. (NEW) A water-soluble polymer dispersion according to Claim 6, wherein the polyalkylenimine and/or modified polyalkylenimine amounts to 20 to 200% by mass relative to the water-soluble polymer having at least one type of ionicity selected from among said cationicity, said amphotericity, said nonionicity and said anionicity.

31. (NEW) A water-soluble polymer dispersion according to Claim 7, wherein the polyalkylenimine and/or modified polyalkylenimine amounts to 20 to 200% by mass relative to the water-soluble polymer having at least one type of ionicity selected from among said cationicity, said amphotericity, said nonionicity and said anionicity.

32. (NEW) A water-soluble polymer dispersion according to Claim 20, wherein the water-soluble polymer having at least one type of ionicity selected from among said anionicity and said nonionicity and occurring in the form of fine particles is produced by dispersion polymerization of a monomer composition (mixture) comprising at least one monomer selected from among monomers represented by said general formula (3) given above and water-soluble nonionic monomers in the presence of said polyalkylenimine and/or modified polyalkylenimine in the sulfate salt form, if necessary further in the presence of a necessary amount of a water-soluble inorganic salt.

33. (NEW) A water-soluble polymer dispersion according to Claim 22, wherein the water-soluble polymer having at least one type of ionicity selected from among said anionicity and said nonionicity and occurring in the form of fine particles is produced by dispersion polymerization of a monomer composition (mixture) comprising at least one monomer selected from among monomers represented by said general formula (3) given above and water-soluble nonionic monomers in the presence of said

polyalkylenimine and/or modified polyalkylenimine in the sulfate salt form, if necessary further in the presence of a necessary amount of a water-soluble inorganic salt.

34. (NEW) A water-soluble polymer dispersion according to Claim 26, wherein the water-soluble polymer having at least one type of ionicity selected from among said anionicity and said nonionicity and occurring in the form of fine particles is produced by dispersion polymerization of a monomer composition (mixture) comprising at least one monomer selected from among monomers represented by said general formula (3) given above and water-soluble nonionic monomers in the presence of said polyalkylenimine and/or modified polyalkylenimine in the sulfate salt form, if necessary further in the presence of a necessary amount of a water-soluble inorganic salt.

35. (NEW) A water-soluble polymer dispersion according to Claim 31, wherein the water-soluble polymer having at least one type of ionicity selected from among said anionicity and said nonionicity and occurring in the form of fine particles is produced by dispersion polymerization of a monomer composition (mixture) comprising at least one monomer selected from among monomers represented by said general formula (3) given above and water-soluble nonionic monomers in the presence of said polyalkylenimine and/or modified polyalkylenimine in the sulfate salt form, if necessary further in the presence of a necessary amount of a water-soluble inorganic salt.